

TECHNICAL INFORMATION

PK 8025-N-UV



Description: Lead free flexible PVC compound

Application: Extrusion hoses and profile, UV resistance

Technical characteristics: CAP FIAT 55251

Property	Test method	Unit	Tolerance	Value
Density(natural colour)	ISO 1183	gr/cm ³	±0,02	1.34
Hardness Shore "A" 15"	ISO 868	point	± 2	80
Tensile strength	ISO 527	N/mm ²	•	15
Elongation at break	ISO 527	%	•	300

The typical values reported in the table have been obtained from measurements made on extruded samples or pressed plates

Storage: compound must be stored at ambient temperature (not exceeding 30°C) in closed and unbroken packaging, in order to avoid exposure to sunlight and water absorption. . Long stocking time may negatively affect the quality of the material. Therefore it shall be used within 12 months from the compounding date. After this deadline it's necessary to dry the material

Packaging: 25Kg plastic bags, big bags, carton oktabins or in silos truck.